

Mechanisms of Deformation Twinning Near Crack Tips in Nanostructured Materials

N.V. Skiba

Institute for Problems in Mechanical Engineering, Russian Academy of Sciences, St. Petersburg 199178, Russia

Received: December 15, 2020

Corresponding author: [N.V. Skiba](#)

Abstract. A brief review of the theoretical models which describe specific mechanisms of deformation twinning near crack tips in nanocrystalline and ultrafine-grained materials is presented. In the first model, formation of deformation twins occurs through emission of twinning dislocations from grain boundaries driven by the external stress concentrated by the pre-existent crack. Within the second model, deformation twins are formed due to ideal nanoshear events initiated by high local stresses in the vicinities of crack tips in nanocrystalline materials. These special mechanisms of deformation twinning near crack tips serve as effective toughening micromechanisms in nanostructured materials.

REFERENCES

- [1] M.A. Meyers, A. Misra and D.J. Benson, *Mechanical properties of nanocrystalline materials*, Progr. Mater. Sci., 2006, vol. 51, no. 4, pp. 427-556.
- [2] M. Dao, L. Lu, R.J. Asaro, J.T.M. De Hosson and E. Ma, *Toward a quantitative understanding of mechanical behavior of nanocrystalline metals*, Acta Mater., 2007, vol. 55, no. 12, pp. 4041-4065.
- [3] C.C. Koch, *Structural nanocrystalline materials: an overview*, J. Mater. Sci., 2007, vol. 42, pp. 1403-1414.
- [4] C.S. Pande and K.P. Cooper, *Nanomechanics of Hall–Petch relationship in nanocrystalline materials*, Progr. Mater. Sci., 2009, vol. 54, no. 6, pp. 689-706.
- [5] Y.T. Zhu, X.Z. Liao and X.L. Wu, *Deformation twinning in nanocrystalline materials*, Progr. Mater. Sci., 2012, vol. 57, no. 1, pp. 1-62.
- [6] H. Abdolvand, K. Louca, C. Mareau, M. Majkut and J. Wright, *On the nucleation of deformation twins at the early stages of plasticity*, Acta Materialia, 2020, vol. 196, pp. 733-746.
- [7] R. Sidharth, W. Abuzaid and H. Sehitoglu, *Nano-twinning enhanced room temperature fatigue crack growth in single crystalline CoCrFeMnNi high entropy alloy*, Intermetallics, 2020, vol. 126, art. 106919.
- [7] T. He and M. Feng, *Effect of nanotwin near a branched crack tip on crack blunting in deformed nanocrystalline materials*, Acta Mechanica, 2018, vol. 229, pp. 3223-3234.
- [8] Z.Y. Liang, J.T.M. De Hosson and M.X. Huang, *Size effect on deformation twinning in face-centred cubic single crystals: Experiments and modelling*, Acta Materialia, 2017, vol. 129, pp. 1-10.

- [9] X.Z. Liao, F. Zhou, E.J. Lavernia, D.W. He and Y.T. Zhu, *Deformation twins in nanocrystalline Al*, Appl. Phys. Lett., 2003, vol. 83, art. 5062.
- [10] M. Chen, E. Ma, K.J. Hemker, H. Sheng, Y. Wang and X. Cheng, *Deformation twinning in nanocrystalline aluminum*, Science, vol. 300, no. 5623, pp. 1275-1277.
- [11] X.Z. Liao, Y.H. Zhao, S.G. Srinivasan, Y.T. Zhu, R.Z. Valiev and D.V. Gunderov, *Deformation twinning in nanocrystalline copper at room temperature and low strain rate*, Appl. Phys. Lett., 2004, vol. 84, no. 4, pp. 592-594.
- [12] Y.M. Wang, A.M. Hodge, J. Biener, A.V. Hamza, D.E. Barnes, K. Liu and T.G. Nieh, *Deformation twinning during nanoindentation of nanocrystalline Ta*, Appl. Phys. Lett., 2005, vol.86, art. 201915.
- [13] M.Y. Gutkin, I.A. Ovid'ko and N.V. Skiba, *Generation of deformation twins in nanocrystalline metals: Theoretical model*, Phys. Rev. B, 2006, vol.74, art. 172107.
- [14] I.A. Ovid'ko and N.V. Skiba, *Nanotwins induced by grain boundary deformation processes in nanomaterial*, Scripta Materialia, 2014, vol. 71, pp. 33-36.
- [15] I.A. Ovid'ko and N.V. Skiba, *Generation of nanoscale deformation twins at locally distorted grain boundaries in nanomaterials*, Int. J. Plasticity, 2014, vol. 62, pp. 50-71.
- [16] I.A. Ovid'ko, *Nanoscale multiplane shear and twin deformation in nanowires and nanocrystalline solids*, Appl. Phys. Lett., 2011, vol. 99, art. 061907.
- [17] I.A. Ovid'ko and A.G. Sheinerman, *Deformation Twinning through Nanoscale Ideal Shears in Nano- and Polycrystalline Materials at Ultra High Stresses*, Rev. Adv. Mater. Sci., 2011, vol. 27, no. 2, pp. 189-194.
- [18] M.Y. Gutkin, I.A. Ovid'ko and N.V. Skiba, *Crack-stimulated generation of deformation twins in nanocrystalline metals and ceramics*, Phil. Mag., 2008, vol. 88, no. 8, pp. 1137-1151.
- [19] N.F. Morozov, I.A. Ovid'ko, A.G. Sheinerman and N.V. Skiba, *Formation of Deformation Twins through Ideal Nanoshear Events near Crack Tips in Deformed Nanocrystalline Materials*, Rev. Adv. Mater. Sci., 2012, vol. 32, no. 1, pp. 75-81.
- [20] M.Yu. Gutkin and I.A. Ovid'ko, *Generation of dislocation loops in deformed nanocrystalline materials*, Phil. Mag., 2006, vol. 86, no. 11, pp. 1483-1511.
- [21] J.P. Hirth and J. Lothe, *Theory of dislocations* (Wiley, New York, 1982).
- [22] R.J. Asaro and S. Suresh, *Mechanistic models for the activation volume and rate sensitivity in metals with nanocrystalline grains and nano-scale twins*, Acta Mater., 2003, vol. 53. no. 12, pp. 3369-3382.
- [23] Z. Ding, S. Zhou and Y. Zhao, *Hardness and fracture toughness of brittle materials: A density functional theory study*, Phys. Rev. B, 2007, vol. 70, art. 184117.
- [24] U. Kaiser and I.I. Khodos, *On the determination of partial dislocation Burgers vectors in fcc lattices and its application to cubic SiC films*, Phil. Mag. A, 2002, vol. 82, no. 3, pp. 541-551.
- [25] A.E. Romanov and A.L. Kolesnikova, *Application of disclination concept to solid structures*, Progr. Mater. Sci., 2009, vol.54, no. 6, pp. 740-769.
- [26] S. Kibey, J.B. Liu, D.D. Johnson and H. Sehitoglu, *Predicting twinning stress in fcc metals: Linking twin-energy pathways to twin nucleation*, Acta Mater., 2007, vol. 55, no. 20, pp. 6843- 6851.
- [27] S.V. Bobylev and I.A. Ovid'ko, *Nanodisturbances and nanoscale deformation twins in fcc nanowires*, Phys. Rev. B, 2011, vol. 83, art. 054111.